

Test Report

Skid Resistance Test

Report: 2022420021
Issued by: Mr. S. Meuwese
Date: October 24, 2022

Client: Recoat B.V.
Product: art. 87662 - Recoat 2K Floor One Plus 10:1

Test Method according to

ISO 13036-4

CONTENTS

1.	TEST MATERIAL	page 2
2.	TEST EQUIPMENT	page 2
3.	TEST RESULTS	page 2-3
4.	CONCLUSION	page 3

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.

1. TEST MATERIAL

Coating:	Recoat 2K Floor One Plus 10:1	MFG:	Dercom B.V.
Batch no.:	N/A	Art. no.:	87662
Substrate:	Recoat Multi Primer	MFG:	Dercom B.V.

2. TEST EQUIPMENT

Type:	Cooper CRT-PENDULUM
Serial No.:	2214-01
Certificate No.:	08 Apr 2022
Calibration date:	CRT/22/5446
Slider:	3.00" Rubber slider 96
Batch No.:	96#13
Certificate No.:	98/12

3. TEST RESULTS

The Pendulum Skid Resistance test has been carried out in eightfold on three different directions of the coating system. The five results which are closest together are used to calculate the average.

Dir. 1	1	2	3	4	5	6	7	8	Mean
Dry	61	63	63	62	61	63	62	62	62
Wet	42	39	39	40	41	40	40	40	40
Dir. 2	1	2	3	4	5	6	7	8	Mean
Dry	61	61	61	62	62	62	61	62	62
Wet	39	39	41	40	40	41	41	40	40
Dir. 3	1	2	3	4	5	6	7	8	Mean
Dry	61	61	63	62	63	63	63	62	63
Wet	41	39	39	39	40	40	40	40	40

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.

Skid resistance test	Average
Dry	62
Wet	40

Potential for slip	Pendulum test values
High slip potential	0 - 24
Moderate slip potential	25 - 35
Low slip potential	36+

4. CONCLUSION

The pendulum test value shows that under dry and wet conditions Recoat 2K Floor One Plus exhibits a **low slip potential**.

Checked and approved by:



Mr. F. Derks
Laboratory R&D management

Our products are suitable for professional use only.

Registered processing times are valid under conditioned application circumstances only. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any date, weights, proportions, etc. given herein are for general information purpose only; they may change without prior information and do not constitute the quality of the products (product specification). For technical support and advice with concern to choices of coatings systems and methods of application our technical staff will be at your service at all times.

Confidentiality

This report and the information therein is strictly confidential and is exclusively intended for the recipient of this report. The recipient of this report will keep all information in it strictly confidential and will not disclose, copy, reproduce or distribute any of it or otherwise make it available to any person or third party without the specific prior written consent of Dercom. The recipient of this report undertakes with Dercom that it will use any of the information in this report for internal purposes only.

Copyright notice

The information in this report is protected by the Dutch Copyright Act and all copyrights are vested in Dercom. The distribution and reproduction of the information in this report without the prior written consent of Dercom is prohibited. © 2021 Dercom.