

König Pendulum Hardness Report

According to ISO-1522 (ASTM D4366)

Date: 10-Feb-20

Name Analyst: Stefan Meuwese

Client: Recoat BV

Test number:2020070029

Material:

Coating:	Recoat 1K Matt	Mfg.	Dercom BV
Batch nr:	N/A	Art nr:	N/A

Substrate material:	Glass	Substrate thickness:	4 mm
Substrate preparation:	Degreased		
Application:	Film applicator		
Curing (time, temp):	72 h @ 20°C (68°F)		
DFT and/or WFT	WFT 90µm		

Sample nr:	measurements			average	Temp.	Humidity
	1	2	3			
1	21	20	21	21	22°C (72°F)	21%RH
Remarks:						